



Optically Brightened Laminating System

Optically brightened with enhanced UV resistance package for white surfboard and marine epoxy applications.

Product Overview BRT is an optically brightened, clear, UV stabilised, general use laminating resin for white surfboard lamination and hot coating. Based on Entropy Resins CLR – Clear Epoxy Resin, BRT can be paired with all CLR Clear Hardeners. BRT is a USDA Certified BioPreferred® Product with 30% biobased content.

	CLX	CLF	CLS
	EXTRA FAST	FAST	SLOW
MECHANICAL DATA			
Tensile Modulus (ASTM D638)	3.1 GPa	3.0 GPa	3.2 GPa
Tensile Strength (ASTM D638)	65.5 MPa	65.5 MPa	67.6 MPa
Elongation (ASTM D638)	6%	5%	6%
Flexural Modulus (ASTM D790)	3.0 GPa	3.0 GPa	3.0 GPa
Flexural Strength (ASTM D790)	96.5 MPa	93.1 MPa	100.5 MPa
Compression Strength (ASTM D695)	78.1 MPa	78.1 MPa	86.3 MPa
Tg Ultimate (DSC, midpoint)	63°C	56°C	57°C
Hardness (Shore D)	70-80	70-80	70-80

PROCESSING DATA			
Mix Ratio (by volume)	2:1	2:1	2:1
Mix Ratio (by weight)	100:45	100:44	100:43
Viscosity (A/B/Mixed @ 25 °C)	2040/180/1160 mPas	2040/280/1100 mPas	2040/140/800 mPas
Component Density (specific density @ 25°C)	1.14 (resin), 0.98 (hardener) gcm ⁻³	1.14 (resin), 1.01 (hardener) gcm ⁻³	1.14 (resin), 0.98 (hardener) gcm ⁻³
Mixed Density (specific density @ 25°C)	1.09 gcm ⁻³	1.10 gcm ⁻³	1.09 gcm ⁻³
Pot Life (@ 25°C)	18 min	21 min	43 min
Tack Free Time (@ 35°C)	2 hrs	4 hrs	8 hrs
Recommended Full Cure	7 days @ 25°C	7 days @ 25°C	7 days @ 25°C, Post cure recommended

ENVIRONMENT DATA				
VOC Content (ASTM D2369)	19.5 g/l	31.5 g/l	0.0 g/l	
Biobased Carbon Content (ASTM D6866)	20%	20%	21%	

These are typical properties and cannot be construed as a specification. The end users should test the products to ensure the products are suitable for the intended application. Any information, data, advice or recommendation published by Wessex Resins or obtained from Wessex Resins by other means and whether relating to Wessex Resins' materials or other materials, is given in good faith and believed to be reliable.

Wessex Resins & Adhesives Ltd. Cupernham House, Cupernham Lane Romsey, Hampshire, SO51 7LF, UK







